


BUTYLEN-AS39 P/-R20 HT



Product information



Special advantages:



For temperatures up to +85°C (+185°F).



Excellent mechanical protection and excellent corrosion prevention.



Proven success for more than 30 years on thousands of kilometres of pipeline.



C50
EN 12068

Fulfills the requirements of EN 12068-C50, DIN 30672-C50 and ISO 21809-3; Type 12A-1.



12A-1
ISO 21809-3

Real co-extruded three-ply tape as the inner layer and two-layer tape as the outer layer.



Compatible with factory coatings made of PE, PP, FBE, PU, CTE and bitumen.

Two-tape system for the corrosion prevention coating of metal pipes and pipelines in accordance with DIN 30672, EN 12068 and ASTM. For extreme corrosion conditions and extreme mechanical stresses – corrosion prevention system with a proven success rate of many thousand kilometers pipeline construction and rehabilitation worldwide.

DEKOTEC GmbH stands for experience, quality and reliability in the field of corrosion prevention and sealing technology. The success is based on the development of the Petrolatum-Tape which was already developed in 1927 as the first product worldwide for passive corrosion prevention of pipelines. We establish and guarantee the highest quality standards with technically trend-setting products. Research, development and production take place exclusively in Germany. Our employees are continuously implementing safe and individual solutions in a personal cooperation with the customer.

Description

BUTYLEN-AS39 P/-R20 HT is a cold applied two-tape system for the corrosion prevention of metal pipes and pipelines in extreme corrosion conditions and mechanical stresses.

Due to the innovative formula, the tapes grow completely together in the overlapping area and create a long-lasting hose-type coating.

BUTYLEN-AS39 P/-R20 HT has proven itself in a multitude of construction projects and has many approvals of pipeline network operators such as Indian Oil Corporation Ltd.

BUTYLEN-AS39 P/-R20 HT is basically impermeable for water vapor and oxygen and it is resistant against soil bacteria and electrolytes.

BUTYLEN-AS39 P/-R20 HT is compatible with factory coatings made of PE, PP, FBE, PU, CTE and Bitumen.

The system **BUTYLEN-AS39 P/-R20 HT** consists of:

BUTYLEN-HT Primer

A solvent containing primer in accordance with EN 12068 and DIN 30672 for the corrosion prevention in combination with **BUTYLEN** tapes.

BUTYLEN-AS39 P


A real co-extruded 3-ply plastic tape made from stabilized polyethylene carrier materials with butyl rubber adhesive on both sides.

BUTYLEN-R20 HT

A real co-extruded two-layer plastic tape made from stabilized polyethylene carrier film with a butyl rubber adhesive on one side. The outstanding connection between the adhesive and the carrier film is guaranteed by the co-extruded intermediate layer. The adhesive layer grows completely together with the outside layer BUTYLEN-AS39 P.



BUTYLEN-AS39 P



BUTYLEN-R20 HT

Typical product properties

Property	Unit	BUTYLEN-AS39 P Typical value	BUTYLEN-R20 HT Typical value	Test method
Carrier film color	-	Black	White, black or blue	-
Butyl adhesive color inside	-	Gray	Black	-
Butyl adhesive color outside	-	Black	-	-
Total thickness	mm	≥0.8	≥0.5	ISO 4591 ASTM D1000
Carrier film thickness app.	mm	≥0.28	≥0.3	
Inside adhesive layer thickness app.	mm	≥0.44	≥0.2	
Outside adhesive layer thickness app.	mm	≥0.08	-	
Elongation at break	%	≥600	≥550	DIN 30672
Tape strength	+23°C (+73°F) N / cm	≥100	≥65	EN 12068
Dielectric strength	kV / mm	≥40	≥35	DIN 53481
Water absorption	+23°C (+73°F) 1 day / 30 days %	≤0.1 / ≤0.4	≤0.1 / ≤0.4	DIN 53495 ASTM D570
Brittleness temperature	°C (°F)	-46±4 (-50.8±7.2)	-46±4 (-50.8±7.2)	DIN 53372
		-58±4 (-72.4±7.2)	-58±4 (-72.4±7.2)	GOST 10354

BUTYLEN-AS39 P/-R20 HT with BUTYLEN-HT Primer

Property	Unit	BUTYLEN-AS39 P/-R20 HT Typical value		Required value		Test method
Electrical insulation resistance	Ohm m ²	≥10 ¹⁰		≥10 ⁸		EN 12068
Contact resistance	Ohm cm	≥10 ¹⁵		Not stated		DIN 53482 ASTM D257
Peel resistance metal/primer/tape	N / cm	+23°C (+73°F)	+50°C (+122°F)	+23°C(+73°F)	+50°C(+122°F)	EN 12068
		≥25	≥3	≥10	≥1	
Peel resistance layer to layer	N / cm	Not stated		Not stated		ASTM D1000
		+23°C (+73°F)	+50°C (+122°F)			
AS39 P / AS39 P	N / cm	≥30	≥4	≥15	≥2	EN 12068
AS39 P / R20 HT		≥30	≥3	≥2	≥2	
R20 HT / R20 HT		≥3	≥3	≥2	≥2	
Indentation resistance - residual layer thickness at stamp load 10 N / mm ² (stamp-Ø 1.8 mm)	mm	+50°C (+122°F)				EN 12068
		≥1.1		≥0.6		
Impact resistance	J	≥16		≥15		EN 12068
Cathodic disbondment resistance	mm	<6		<20		EN 12068
Lap shear strength	N / cm ²	+23°C (+73°F)				EN 12068
		on steel		5		
		on factory coating		5		

BUTYLEN tapes can be easily applied manually. The processing with the original **DEKOMAT**[®] wrapping devices is even more efficient. For **BUTYLEN** tapes with widths of > 50 mm, we recommend the use of the **DEKOMAT**[®] wrapping device to guarantee an excellent processing quality.

Ordering information and packaging

		Width [mm]	Length [m]	m ² / roll	Content per box			
					Rolls	m ²	Lfd.. m	kg (app.)
BUTYLEN-AS39 P	Core Ø 41 mm	50	15	0.75	12	9	180	9.0
		100	15	1.5	6	9	90	10.2
		150	15	2.25	6	13.5	90	13.0
	Core Ø 78 mm	100	70	7	3	21	210	19.0
		150	70	10.5	2	21	140	19.0
BUTYLEN-R20 HT	Core Ø 41 mm	50	30	1.5	12	18	360	11.0
		100	30	3.0	6	18	180	11.0
		150	30	4.5	6	27	180	17.0
	Core Ø78 mm	100	70	7	3	21	210	13.0
		150	70	10.5	2	21	140	13.0

Additional lengths and widths are available on request.

Storage

When stored in its original, unopened packaging, **BUTYLEN-AS39 P/-R20 HT** can be stored for at least 60 months after the manufacturing date.

Storage temperature: ≤ +50°C (+122°F)

Store in a dry location and do not rest anything against the front of the product.

DEKOTEC GmbH

Felderstrasse 24 | 51371 Leverkusen | Germany
Phone: +49 214 2602-0 | info@dekotec.com
www.dekotec.com

Our product information, application recommendations and other printed publications provide advice to the best of our knowledge and indicate our level of knowledge at the time of printing. The content is not legally binding. Therefore, no liability is assumed for incorrect and missing advice. The applicator is obliged to check the suitability and possibility of application for the intended purpose. Unless otherwise specified, all of the brands named are trademarks, at least registered in Germany, which are protected by law.

Only our general terms and conditions of sale, which you will find at www.dekotec.com, apply. This is a translation from the original German product information. In case of any discrepancy or any dispute arising on the interpretation, the German text of the respective German product information, shall be decisive. The legal relationship shall be governed by German law.

05.2021