


BUTYLEN-N15/-PE5



Product information



Special advantages:

- ✓ Especially thick and adaptable inner layer made from butyl rubber tape with a thickness of 1.5mm.
- ✓ Ideal for uneven surfaces.
- ✓ Excellent corrosion protection and exceptionally easy to apply.
- ✓ **C30**
EN 12068 Fulfills EN 12068-C30 and DIN 30672-C30.
- ✓ Compatible with factory coatings made of PE, PP, FBE, PU, CTE and bitumen.

Two-tape system for the corrosion prevention coating of metal pipes, pipelines and containers in accordance with DIN 30672, EN 12068, ASTM and AWWA. For extreme corrosion conditions and mechanical stresses on uneven substrates.

DEKOTEC GmbH stands for experience, quality and reliability in the field of corrosion prevention and sealing technology. The success is based on the development of the Petrolatum-Tape which was already developed in 1927 as the first product worldwide for passive corrosion prevention of pipelines. We establish and guarantee the highest quality standards with technically trend-setting products. Research, development and production take place exclusively in Germany. Our employees are continuously implementing safe and individual solutions in a personal cooperation with the customer.

Description

BUTYLEN-N15/-PE5 is a cold applied two-tape system for corrosion prevention of metal pipes and moldings with special qualification for the application of uneven substrates and complicated geometries.

A flexible butyl rubber adhesive layer with a thickness of 1.5 mm makes it possible for **BUTYLEN-N15** to adapt optimally to uneven substrates even with complicated geometries.

BUTYLEN-N15/-PE5 is essentially impermeable for water vapor and oxygen and it is resistant against soil bacteria and electrolytes.

BUTYLEN-N15/-PE5 is compatible with factory coatings made of PE, PP, FBE, PU, CTE and Bitumen.

The system BUTYLEN-N15/-PE5 consists of: **BUTYLEN-HT Primer** is a solvent containing primer in accordance with EN 12068 and DIN 30672 for corrosion prevention with **BUTYLEN** tapes. Please refer to the separate product information of the BUTYLEN-HT Primer.

BUTYLEN-N15 is a real co-extruded 3-ply butyl rubber tape with butyl rubber adhesive on both sides and a carrier film made from stabilized polyethylene film. BUTYLEN-N15 has a thickness of ≥ 1.5 mm. BUTYLEN-N15 fulfills the international standards DIN 30672, EN 12068, ASTM and AWWA.

BUTYLEN-PE5 is a real co-extruded two-ply plastic tape made from stabilized black polyethylene carrier film with a butyl rubber adhesive on one side. The thickness is ≥ 0.5 mm.

Outstanding connection between the adhesive and the carrier film due to the co-extruded intermediate layer. The adhesive layer grows completely together with the outside layer of BUTYLEN-N15. BUTYLEN-PE5 fulfills the international standards DIN 30672, EN 12068, ASTM and AWWA.

Typical product properties

Property	Unit	BUTYLEN-N15 Typical value	BUTYLEN-PE5 Typical value	Test method
Carrier film color	-	black	black	-
Butyl adhesive color inside	-	grey	grey	-
Butyl adhesive color outside	-	grey	-	-
Total thickness	mm	≥ 1.5	≥ 0.5	ISO 4591 ASTM D1000
Carrier film thickness app.	mm	≥ 0.07	≥ 0.3	
Inside adhesive layer thickness app.	mm	≥ 0.75	≥ 0.2	
Outside adhesive layer thickness app.	mm	≥ 0.68	-	
Elongation at break	%	-	≥ 450	DIN 30672
Tape strength	+23°C (+73°F) N / cm	-	≥ 60	EN 12068
Dielectric strength	kV / mm	≥ 40	≥ 40	DIN 53481
Water absorption	+23°C (+73°F) 1 day / 30 days %	≤ 0.1 / ≤ 0.4	≤ 0.1 / ≤ 0.4	DIN 53495 ASTM D570
Brittleness temperature	°C	-46±4 (-50.8±7.2)	-46±4 (-50.8±7.2)	DIN 53372
		-58±4 (-72.4±7.2)	-58±4 (-72.4±7.2)	GOST 10354

BUTYLEN-N15/-PE5 (2+2 layers) with BUTYLEN-HT Primer

Property	Unit	BUTYLEN-N15/-PE5 Typical value		Required value	Test method
Specific electrical insulation resistance	Ohm m ²	≥ 10 ¹²		≥ 10 ⁸	EN 12068
Volume resistivity	Ohm cm	≥ 10 ¹⁵		Not stated	DIN 53482 ASTM D257
Peel strength metal/primer/tape	N / cm	+23°C (+73°F)	+30°C (+86°F)	≥ 10 ≥ 1	EN 12068 ASTM D1000
		≥ 15	≥ 1.5		
Peel strength layer to layer	N / cm	+23°C (+73°F)	+30°C (+86°F)	≥ 10 ≥ 2	EN 12068
		≥ 15	≥ 2		
N15 / N15	mm / N/mm ²	≥ 30	≥ 2	≥ 10 ≥ 2	EN 12068
N15 / PE5		≥ 15	≥ 2	≥ 10 ≥ 2	
PE5 / PE5		≥ 2	≥ 2	≥ 2 ≥ 2	
Indentation resistance - residual layer thickness for stamp load (stamp-Ø 1.8 mm)	mm / N/mm ²	+30°C (+86°F)		> 0.6	EN 12068
		≥ 0.6			
Impact resistance	J	≥ 15		≥ 15	EN 12068
Cathodic disbondment resistance	mm	≤ 10		Not stated	ASTM G8
Total system thickness	mm	≥ 4.00		Not stated	ISO 4591 ASTM D1000
2 layers BUTYLEN-N15		≥ 3.00			
2 layers BUTYLEN-PE5		≥ 1.00			
Lap shear strength	on steel N/cm ²	≥ 10		≥ 5	EN 12068

BUTYLEN tapes can be easily applied manually. The processing with the original **DEKOMAT**[®] wrapping devices is even more efficient. For **BUTYLEN** tapes with widths of > 50 mm, we recommend the use of the **DEKOMAT**[®] wrapping device to guarantee an excellent processing quality.

Ordering information and packaging

	Core diameter (mm)	Width (mm)	Tape length (m)	Tape area (m ²)	Content per box			
					Number of rolls	Total tape area (m ²)	Total tape length (m)	App. Weight (kg)
BUTYLEN-N15	41	30	7.5	0.225	18	4.05	135	9.5
		50	7.5	0.375	12	4.5	90	10.5
		100	7.5	0.75	6	4.5	45	10.5
		150	7.5	1.125	6	6.75	45	15.5
BUTYLEN-PE5	41	30	15	0.45	18	8.1	270	6.0
		50	15	0.75	12	9.0	180	6.0
		50	30	1.5	12	18.0	360	11.0
		100	30	3	6	18.0	180	11.0
		150	30	4.5	6	27.0	180	16.5

Additional lengths and widths are available on request.

Storage

When stored in its original, unopened packaging, **BUTYLEN-N15/-PE5** can be stored for at least 60 months after the manufacturing date.

Storage temperature: ≤ +50°C (+122°F)

Store in a dry location and do not rest anything against the front of the product.

DEKOTEC GmbH

Felderstrasse 24 | 51371 Leverkusen | Germany
Phone: +49 214 2602-0 | info@dekotec.com
www.dekotec.com

Our product information, application recommendations and other printed publications provide advice to the best of our knowledge and indicate our level of knowledge at the time of printing. The content is not legally binding. Therefore, no liability is assumed for incorrect and missing advice. The applicator is obliged to check the suitability and possibility of application for the intended purpose. Unless otherwise specified, all of the brands named are trademarks, at least registered in Germany, which are protected by law.

Only our general terms and conditions of sale, which you will find at www.dekotec.com, apply. This is a translation from the original German product information. In case of any discrepancy or any dispute arising on the interpretation, the German text of the respective German product information, shall be decisive. The legal relationship shall be governed by German law.