


BUTYLEN-PE5

Product information



Special advantages:

- ✓ Certified by DVGW in combination with BUTYLEN-N15.
- ✓ Genuine co-extruded two-layer tape.
- ✓ Flexible mechanical protective tape.
- ✓ Compatible with factory coatings made from PE, PP, FBE, PU, CTE and bitumen.

Co-extruded 2-ply plastic tape, made from a stabilized polyethylene carrier material and with a one-sided butyl rubber coating.

DEKOTEC GmbH stands for experience, quality and reliability in the field of corrosion prevention and sealing technology. The success is based on the development of the Petrolatum-Tape which was already developed in 1927 as the first product worldwide for passive corrosion prevention of pipelines. We establish and guarantee the highest quality standards with technically trend-setting products. Research, development and production take place exclusively in Germany. Our employees are continuously implementing safe and individual solutions in a personal cooperation with the customer.

Description

BUTYLEN-PE5 is a genuine co-extruded 2-layer plastic tape, made from a stabilized black polyethylene carrier material and with a butyl rubber coating on one side. The tape thickness is ≥ 0.5 mm.

BUTYLEN-PE5 can be applied cold and is used as a mechanical protective tape for corrosion protection wrapping applied in

combination with **BUTYLEN 3**-layer polymeric tapes.

BUTYLEN-PE5 acts as an outer tape component in the tape system **BUTYLEN-N15/-PE5**, which holds DVGW certification for the stress class C 30 as defined by DIN EN 12068. The tape system **BUTYLEN-N15/-PE5** is ideally suited for use in the corrosion

protection of metal pipes and pipe fittings with complex geometries.

BUTYLEN-PE5 is compatible with factory coatings made from PE, PP, FBE, PU, CTE and bitumen.

BUTYLEN-PE5 can be processed efficiently with **DEKOMAT®** wrapping machines.

Typical product properties

Property	Unit	Typical value	Test method
Carrier film color	-	black	-
Butyl adhesive color (inner)	-	grey	-
Tape thickness	mm	≥ 0.5	ISO 4591 ASTM D1000
Carrier film thickness (approx.)	mm	≥ 0.3	
Inner adhesive layer thickness (approx.)	mm	≥ 0.2	
Outer adhesive layer thickness (approx.)	mm	-	
Elongation at break	%	≥ 450	DIN 30672
Tensile strength	+23°C (+73°F) N/cm	≥ 60	DIN 30672
Dielectric strength	kV/mm	≥ 40	DIN 53481
Water absorption	+23°C (+73°F) 1 day/30 days %	≤ 0.1 / ≤ 0.4	-
Operating temperature	°C (°F)	-40 to +50 (-40 to +122)	-

BUTYLEN tapes can easily be applied by hand. Application is even more efficient with original **DEKOMAT**[®] wrapping machines. For **BUTYLEN** tapes with widths >50 mm, we recommend the deployment of a **DEKOMAT**[®] wrapping machine, to ensure that the final workmanship is of a superior and uniform quality.

Ordering information and packaging

	Core diameter (mm)	Tape length (m)	Roll width (mm)	Box contents			Weight per box (kg) (approx.)
				Number of rolls	Total tape length (m)	Total tape area (m ²)	
BUTYLEN-PE5	41	15	30	18	270	8.1	6
			50	12	180	9	6
		30	50	12	360	18	11
			100	6	180	18	11
			150	6	180	27	16.5

Other dimensions available on request.

Storage

When stored in its original, unopened packaging, **BUTYLEN-PE5** can be stored for at least 60 months after the manufacturing date.

Storage temperature: ≤ +50°C (+122°F)

Store in a dry location and do not rest anything against the front of the product.

DEKOTEC GmbH

P.O. Box 150120 | 51344 Leverkusen | Germany

Phone: +49 214 2602-0

www.dekotec.com | info@dekotec.com

Our product information, our application recommendations and other product related documents are made for your convenience only.

Since many installation factors are beyond our control, the user shall determine the suitability of the products for the intended use and assume all risks and liabilities in connection therewith.

All information contained in this document is to be used as a guide and does not constitute a warranty of specification. The information contained in the document is subject to change without notice. For this reason, no liability can be accepted for inaccurate advice or any failure to provide advice.

The user is responsible for checking the applications of the product and verifying its suitability for the intended use.

Our General Terms of Sale, which are available at www.dekotec.com, shall be decisive without any exception.

This is a translation from the original German product information.

In case of any discrepancy or any dispute arising on the interpretation of this product information, the German text of the respective German product information, which is available at www.denso-group.com, shall be decisive. The legal relationship shall be governed by German law.