


BUTYLEN-System 4

BUTYLEN-032-65 AS/-090

Product information



Special advantages:



For operating temperatures up to +50°C (+122°F).



Fulfills EN 12068-C 50.



Optimal for the coating of moulded parts.

Robust two-tape field coating system for the corrosion prevention of pipelines and pipeline components.

DEKOTEC GmbH stands for experience, quality and reliability in the field of corrosion prevention and sealing technology. The success is based on the development of the Petrolatum-Tape which was already developed in 1927 as the first product worldwide for passive corrosion prevention of pipelines. We establish and guarantee the highest quality standards with technically trend-setting products. Research, development and production take place exclusively in Germany. Our employees are continuously implementing safe and individual solutions in a personal cooperation with the customer.

Description

BUTYLEN System 4 is a two-tape field coating system for the permanent corrosion prevention of pipelines and pipeline components. BUTYLEN System 4 due to its design of two thin and well formable **BUTYLEN** tapes is optimally qualified for the encasement of pipeline components such as T-fittings, flanges, sleeves or pipe elbows with small nominal pipe size. Based on the multi-layer design, a coating system is created for high mechanical and corrosive stresses.

BUTYLEN System 4 features an ÖVGW approval for stress class C 50 in accordance with EN 12068.

Standard designation:

- EN 12068 - C 50



BUTYLEN System 4 consists of the following **BUTYLEN** tapes:

BUTYLEN-032-65 AS as the inside tape, assumes the major corrosion prevention properties of the system.

BUTYLEN-032-65 AS is a co-extruded 3-ply tape with an asymmetrical layer design. This design with a relative thin tape thickness of 0.65 mm provides nevertheless a thick butyl rubber coating on the pipe surface and therefore it provides an outstanding adhesive connection even if the pipe surface is uneven.

Due to the butyl rubber layer at the upper side of the tape, a self-amalgamation effect will be achieved in the overlapping area and an essentially gas and watertight as well as electrically high insulating encasement will be created.

In the BUTYLEN System 4, BUTYLEN-032-65 AS is used as corrosion prevention tape (winding with $\geq 50\%$ overlapping) as well as a tensioning tape (winding with $\geq 66\%$ overlapping).

BUTYLEN-090 is used as the outside tape in the encasement system. BUTYLEN-090 is a flexible two-ply tape with a polyethylene outside layer and an inside butyl rubber adhesive, which welds together with the outside layer of the inner tape. BUTYLEN-090 acts as mechanical protection layer for the corrosion prevention tape located on the inside.

Both **BUTYLEN** tapes can be processed efficiently with the **DEKOMAT®** wrapping devices.

Typical product properties

Property	Unit	BUTYLEN-032-65 AS Typical value	BUTYLEN-090 Typical value	Test method
Carrier film color	-	black	yellow	-
Butyl adhesive color inside	-	grey	grey	-
Butyl adhesive color outside	-	black	-	-
Tape thickness	mm	≥0.65	≥0.4	ISO 4591 ASTM D1000
Carrier film thickness app.	mm	≥0.18	≥0.26	
Inside adhesive layer thickness app.	mm	≥0.39	≥0.14	
Outside adhesive layer thickness app.	mm	≥0.08	-	
Elongation at break	%	≥550	≥400	DIN 30672
Tape strength	+23°C (+73°F) N/cm	≥50	≥35	EN 12068
Dielectric strength	kV/mm	-	-	ASTM D149

Property	Unit	BUTYLEN System 4 Typical value	Required value	Test method
System design	Primer	BUTYLEN-HT Primer	-	-
	Inside tape	BUTYLEN-032-65 AS, 2 layers	-	-
	Tensioning tape	BUTYLEN-032-65 AS, 3 layers	-	-
	Outside tape	BUTYLEN-090, 2 layers	-	-
Total thickness	mm	≥4.1	-	-
Specific electrical insulation resistance	Ohm m ²	≥10 ¹⁰	≥10 ⁸	EN 12068
Peel strength on steel	+23°C (+73°F)	≥15	≥10	EN 12068
	+50°C (+122°F)	≥2	≥1	
Peel strength on PE	+23°C (+73°F)	≥10	≥4	EN 12068
Peel strength layer to layer	032-65 AS / 032-65 AS	≥22	≥15	EN 12068
	032-65 AS / 090	≥22	≥15	
	090 / 090	≥2	≥2	
Indentation resistance (residual layer thickness)	+23°C (+73°F) (10 MPa)	≥0.8	≥0.6	EN 12068
Impact resistance	J	≥15	≥15	EN 12068
Cathodic disbondment resistance	mm	<2	<20	EN 12068
Lap shear strength	on steel N/cm ²	≥8	≥5	EN 12068

BUTYLEN tapes can be easily applied manually. The processing with the original **DEKOMAT**[®] wrapping devices is even more efficient. For **BUTYLEN** tapes with widths of > 50 mm, we recommend the use of the **DEKOMAT**[®] wrapping device to guarantee an excellent processing quality.

Ordering information and packaging

	Core diameter (mm)	Tape length (m)	Width (mm)	Tape area (m ²)	Content per box			
					Number of rolls	Total tape area (m ²)	Total tape length (m)	App. weight (kg)
BUTYLEN-032-65 AS	41	15	30	0.45	18	8.1	270	6
			50	0.75	12	9.0	180	6.5
			75	1.125	12	13.5	180	10.0
			100	1.5	6	9.0	90	6.5
BUTYLEN-090	41	15	50	0.75	12	9.0	180	6,5
			75	1.125	12	13.5	180	10.0
			100	1.5	6	9.0	90	6,5

Additional lengths and widths are available on request.

Storage

When stored in its original, unopened packaging, **BUTYLEN-032-65 AS/090** can be stored for at least 60 months after the manufacturing date.

Storage temperature: ≤ +50°C (+122°F)

Store in a dry location and do not rest anything against the front of the product.

DEKOTEC GmbH

Felderstrasse 24 | 51371 Leverkusen | Germany
Phone: +49 214 2602-0 | info@dekotec.com
www.dekotec.com

Our product information, application recommendations and other printed publications provide advice to the best of our knowledge and indicate our level of knowledge at the time of printing. The content is not legally binding. Therefore, no liability is assumed for incorrect and missing advice. The applicator is obliged to check the suitability and possibility of application for the intended purpose. Unless otherwise specified, all of the brands named are trademarks, at least registered in Germany, which are protected by law.

Only our general terms and conditions of sale, which you will find at www.dekotec.com, apply. This is a translation from the original German product information. In case of any discrepancy or any dispute arising on the interpretation, the German text of the respective German product information, shall be decisive. The legal relationship shall be governed by German law.

06.2022