







Special Advantages:

-  Rapid working and material hardening – roads can be re-opened to traffic quickly.
-  Good mechanical abrasion resistance.
-  Very good compound adhesion to asphalt.
-  Due to the material consistency, cavities in porous asphalt remain open.
-  Ideal pack size – also suitable for small repairs.
-  Roads can quickly be re-opened for traffic.

Innovative, two-component cold-worked repair compound. Especially suitable for repairing surface damage – such as scoring after tyre blowouts, for example – in porous and conventional asphalt wearing courses.

DEKOTEC GmbH stands for experience, quality and reliability in the field of corrosion prevention and sealing technology. The success is based on the development of the Petrolatum-Tape which was already developed in 1927 as the first product worldwide for passive corrosion prevention of pipelines. We establish and guarantee the highest quality standards with technically trend-setting products. Research, development and production take place exclusively in Germany. Our employees are continuously implementing safe and individual solutions in a personal cooperation with the customer.

Product Description

Incidents of mechanical damage occur over and over again, particularly in porous asphalt wearing courses.

Grooving frequently occurs when tyres are damaged on HGVs and the rims are dragged over the asphalt from full speed to a complete stop. Such grooves can be up to 3 cm wide and approx. 1-3 cm deep. Such damage to the surface can have an adverse

effect on traffic safety, while also acting as a starting point for further, more serious damage to the wearing course.

TOK®-Rep now gives you the option of quickly and safely remedying such damage in order to avoid any further deterioration in surface quality.

With porous asphalt wearing courses, care must be taken to leave a sufficiently porous

area of the wearing course under the scoring to allow water to drain off.

If the surface damage is serious enough to prevent repairs being carried out using this compound, we recommend milling off the damaged area and installing a new surface.

The proper joint connections can then be created using our special joint tape, **TOK®-Band SK Drain**.

Typical Material Properties (at +23 °C/+73.4 °F)

Technical data	Unit	Value
Density (A+B, hardened)	kg/l	1.45 (approx.)
Colour	-	Black
Mixing ratio (A:B, parts by weight)	-	4:1
Pot life	Minutes	4-6 minutes (approx.)

Product Application

Preparation of the damaged areas

The contact surfaces must be clean and dry. Loose aggregate components must be removed. The damaged areas (for purely aesthetic reasons) can be masked at the sides with masking tape.

Working the compound

Components A and B are mixed together with a mixer (e.g. drill with mixing blade Collomix WK 70) for 1–2 minutes at a rotation speed of max. 500 rpm (ensure that as little air as possible is introduced into the mixture).

The A component should be first stirred separately.

The container pairs (A+B) must be added together as they were assembled and delivered in the box, so that the required mixing ratio is observed.

The mixed material is cast immediately afterwards.

The surface temperature of the asphalt must be at least +5 °C and at most max. +40 °C (+41 °F to +104 °F).

The dew point must be observed.

Any rising air bubbles must be removed (e.g. by painting over with a brush, or by briefly scorching with a gas burner) before the compound solidifies.

The installed compound can then be smoothed off and levelled with a trowel.

To achieve sufficient



surface grip, it is necessary to sprinkle the compound with an excess of grit after it has been poured. For this, we recommend a grit with a PSV value (Polished Stone Value) of 40 to 60, grain size approx. 0/5. It is vital to ensure that the grit is dry when applied.

If the grit is damp, the fresh

TOK®-Rep can foam up under certain circumstances.

Depending on the weather, the material must be kept dry for 10 to 20 minutes after it has been installed (at +23 °C/+73.4 °F).

The material should then be protected as far as possible from moisture until it hardens.



The masking tape applied to the sides of the repair area should be removed immediately after pouring and gritting. Approx. 60 minutes after application (at +23 °C/+73.4 °F), the compound is usually hardened to an extent where the road can be reopened to traffic.

After approx. 24 hours (at approx. +23 °C/+73.4 °F), the compound is tack-free and completely hardened. The pot life and hardening time are temperature dependent. They shorten at higher temperatures and lengthen at lower temperatures.

Cleaning tools

Tools and working equipment can be cleaned using acetone.

Already-hardened material can be removed mechanically.

Ordering Information and Packaging

TOK®-Rep is delivered as a set with components A and B in a box.

The content of the components A and B corresponds to the respective mixing ratio.

There are 48 sets (equal to 96 litres) packed on a pallet.

Product name	Pack size	Order number
TOK®-Rep	2.0 l (A+B components), 96 litres per pallet	on enquiry

Storage

TOK®-Rep must be stored sealed in its original containers.

In all cases, avoid exposing the compounds to temperatures over

+40 °C (+104 °F) and frost – both in storage and on the building site.

Under these conditions,

TOK®-Rep can be stored for at least 12 months from the date of manufacture.

DEKOTEC GmbH

Felderstrasse 24 | 51371 Leverkusen | Germany
Phone: +49 214 2602-0 | info@dekotec.com
www.dekotec.com

Our product information, application recommendations and other printed publications provide advice to the best of our knowledge and indicate our level of knowledge at the time of printing. The content is not legally binding. Therefore, no liability is assumed for incorrect and missing advice. The applicator is obliged to check the suitability and possibility of application for the intended purpose. Unless otherwise specified, all of the brands named are trademarks, at least registered in Germany, which are protected by law.

Only our general terms and conditions of sale, which you will find at www.dekotec.com, apply. This is a translation from the original German product information. In case of any discrepancy or any dispute arising on the interpretation, the German text of the respective German product information, shall be decisive. The legal relationship shall be governed by German law.

08.2022